



TECHNICAL DATA

Heavy Duty Backing Grout

Epirez[®] 5137

Description

Heavy Duty Backing Grout (5137) is a non-shrink, heavy duty epoxy grout. It will flow into fine voids and cavities down to 2mm and harden to produce an extremely tough, impact resistant backing.

Heavy Duty Backing Grout (5137) is recommended as a backing grout for crusher manganese steel liners. It provides immediate and effective support to the components, as well as maximum protection for supporting structures throughout the life of the liner.

Heavy Duty Backing Grout (5137) has been chosen by major mining and quarrying operators for over 25 years throughout Australia, Asia and the Pacific region.

Areas of application

- Long life backing of crushing equipment
- High strength bearing supports
- Grouting of machine bases in corrosive environments
- Grouting of bridge footings
- Rail grouting

Features

- Non shrink
- Excellent mechanical strength
- Easy mixing – no aggregate
- Good chemical resistance
- Excellent flow characteristics
- High compressive strength
- Suitable for pours* from 2mm to 50mm

*Dependent on volume of pour, please consult ITW Polymers & Fluids Technical Department for specific recommendations.

The information contained in this Technical Bulletin is as up to date and correct as possible as at the time of issue. The data provided should be used as a guide only as the performance of the product will vary depending on differing operating conditions and application methods.

The sale of any product described in this Technical Bulletin will be in accordance with ITW Polymers & Fluids Conditions Of Sale, a copy of which is available on request. To the extent permitted by law, ITW Polymers & Fluids excludes all other warranties in relation to this product.

General Properties

Shelf Life	: 2 Years
Mixing Proportions by Weight	: 1 Hardener to 10 Compound
Mixing Proportions by Volume	: 1 Hardener to 5 Compound
Initial Mixed Viscosity, 25°C	: < 10 Pa.s
Colour when mixed	: Olive Green
Work Time of 10kg Mix, 25°C	: 30 minutes
15°C	: 60 minutes
Setting Time, 25°C	: 6 hours
15°C	: 12 hours
Cure Time, 25°C	: 24 hours
15°C	: 48 hours
Maximum Casting Thickness	: 50mm
Compressive Strength	: 124 MPa
Compressive Modulus	: 4.7 GPa
Elongation at Break	: 1%
Tensile Modulus	: 2.9 GPa
Brinell Hardness	: 57
Maximum Service Temperature	: 130°C
Flammability ASTM D 635	: Self extinguishing
Dielectric Constant, 100 kHz, 25°C	: 3.3
Dielectric Strength	: 180 kV/cm

Estimating Data

10 kg Heavy Duty Backing Grout (5137) = 6 Litres

Application Directions

Prepare surfaces for adhesion or release as desired. New concrete should be at least 28 days old. Formwork which provides a "head" of material will facilitate flow into finer cavities and voids. Pour contents of Hardener into Compound container and mix thoroughly for 5 minutes using a suitable blade fitted to a 400 rpm power mixer. Ensure that all the material on the sides and on the bottom of the container is incorporated. DO NOT AERATE. Pour mixed material slowly, from one side only, so as to avoid air entrapment.

Surface preparation guidelines cannot cover all site or field contingencies and it is always recommended that an on-the-spot adhesion test be performed as part of the Standard Quality Assurance audit for the project.

Cleaning

Tools and equipment may be cleaned before hardening commences by washing in **Epirez® Clean Up Solvent**. Do not use for cleaning hands or mixing with product.

Limitations

Heavy Duty Backing Grout (5137) should not be applied at temperatures below 10°C.

Storage and Shelf life

Store in dry conditions between 10°C and 30°C, away from sources of heat and naked flames. Protect from frost. When stored in original containers the minimum shelf life is 2 years.

AUSTRALIA

ITW Polymers & Fluids
100 Hassall Street
Wetherill Park NSW 2164
Phone (02) 9757 8800 Fax (02) 9757 3855

NEW ZEALAND

ITW Polymers & Fluids
Unit 2 / 38 Trugood Drive
East Tamaki 2013, Auckland
Phone (09) 272 1945 Fax (09) 273 6489

Packaging

Heavy Duty Backing Grout (5137) is available in 10kg kits. A kit contains the Hardener and Compound in correct proportions for use.

Ordering Information:

10kg #E951377

Note

The figures quoted for work time, setting time and cure time are not definitive. They are dependent on job site conditions and will vary accordingly. In all cases we endeavour to provide typical figures for use as a guide.

Health & Safety Information

The product is hazardous. A Material Safety Data Sheet is available from the ITW Polymers & Fluids Technical Department upon request or available on our website www.epirez.com.au.

AUSTRALIA

ITW Polymers & Fluids
100 Hassall Street
Wetherill Park NSW 2164
Phone (02) 9757 8800 Fax (02) 9757 3855

NEW ZEALAND

ITW Polymers & Fluids
Unit 2 / 38 Trugood Drive
East Tamaki 2013, Auckland
Phone (09) 272 1945 Fax (09) 273 6489