

DENSO COVERCOAT/BASECOAT KIT

Tough, Protective Outer Coating

Description

Denso Covercoat/Basecoat Kit is a two component, hard wearing coating, consisting of a liquid portion containing synthetic polymers, waterproofing admixtures and a cementitious powder portion consisting of fine fillers.

Uses

Denso Basecoat Kit in conjunction with a suitable scrim (Denso D10 Scrim) is used to provide a tough protective outer coating over Denso Petrolatum Tapes and as the saturation coat on Denso Fabric Backed Tapes.

Features

- Durable and weatherproof
- Excellent flexibility
- Good resistance to moderate trafficking
- Application by brush or roller

Application

Denso Covercoat/Basecoat shall be applied over Denso Petrolatum Tape or Fabric Backed Tapes.

Add component A (grey powder) to Component B (white liquid), whilst being thoroughly mixed using a wooden mixing stick or spatula. Keep mixing the solution until all the powder has been added and the mixture takes on a smooth slurry texture. The Denso Covercoat/Basecoat should be re-mixed every 10 to 15 minutes to ensure that there is no settling out or separation between the two components.

Seal the applied Petrolatum or Fabric Tape by applying a liberal coat of Denso Covercoat/Basecoat to take on a copper appearance. The Denso Petrolatum or Fabric Tape is further protected and reinforced by another liberal amount of Denso Covercoat/Basecoat, immediately followed by a circumferential wrap of Denso D10 Scrim, allowing a minimum of 75 mm overlap. As application proceeds, continue to saturate the scrim by brush with Denso Covercoat/Basecoat. Nominal coverage of the Denso Covercoat/Basecoat is 1.3 L/m².

Allow Denso Covercoat/Basecoat to cure for a further 12 hours before applying a suitable Denso Topcoat. Lightly abrade Denso Covercoat/Basecoat prior to application of Topcoat.



Denso Covercoat/Basecoat Kit

Property Specifications

PROPERTIES	VALUE
% Solids	33%
Specific Gravity @ 25°C	0.99
Drying Time	2 h @ 25°C
Flash Point	38°C
Temperature Range	
For Application	0°C - 50°C
For Continuous Service	-30°C - 60°C
Product Size	6 kg kit (2.5 kg - Liquid, 3.5 kg powder)

STORAGE: Keep in cool, dry ambient conditions and away from heat and direct sunlight.



DENSO (AUSTRALIA) PTY LTD
77 - 95 National Boulevard
Campbellfield, VIC 3061
Tel: +61 3 9356 7600
Fax: +61 3 9356 7699

www.densoaustralia.com.au

A Member of the Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.