

High flow, dual shrinkage compensated, precision cementitious grout

Uses

General grouting of gaps from 10mm to 100mm, where high flow is required along with dual shrinkage compensation (previously Class A/Class C). Applications include grouting of:

- Baseplates and soleplates of machines
- Structural steel column baseplates
- Voids between precast concrete and infilling blockwork

Advantages

- Dual expansion system compensates for shrinkage in both the plastic and hardened states
- High ultimate strength and low permeability ensure the durability of the hardened grout
- Can be dry packed/rammed, trowelled, flowed and pumped
- Hydrogen free gas expansion
- Prepackaged material overcomes potential on-site mixing variations
- No metallic iron content to cause rusting

Properties

| Test Method | Standard | Result | | | | |
|---|----------------------------------|--|-------------------------------|-------|--------|---------|
| Compressive Strength | AS 1478.2:2005 | Consistency | Water Addition | 1 Day | 7 Days | 28 Days |
| | | Stiff | 2.6-3.4 | 45 | 60 | 70 |
| | | Plastic | 3.4-3.6 | 35 | 50 | 60 |
| | | Flowable | 3.6-3.9 | 25 | 45 | 55 |
| Flexural Strength (Modulus of Rupture) | AS 1012.11 - 2000 | 1 Day 7 Days 28 Days | 5.0 MPa 9.5 MPa 9.6 MPa | | | |
| Indirect Tensile Strength | AS 1012.10.2000 | 1 Day 7 Days 28 Days | 2.7 MPa 4.4 MPa 4.8 MPa | | | |
| Setting Time | AS 1012.18:1996 | 5.5 hours - initial set 7.5 hours - final set | | | | |
| Fresh Wet Density | | 2200 kg/m ³ - depending on consistency used | | | | |
| Alkali reactive particles | Rapid Mortar Bar Test (RTA T363) | Non-reactive | | | | |
| Flow Characteristics | AS 1478.2:2005 | 400 - 600mm (Flow Trough) | | | | |
| Minimum Thickness | | 10mm | | | | |
| Maximum Thickness | | 100mm | | | | |

Clarification of property values: The typical properties given above are derived from laboratory testing at 23°C. Compressive strengths stated above were measured using cube samples. Test results obtained will vary if carried out to an alternative standard or sample dimensions are used.

Note: Compressive strengths stated were measured at bottom end water, eg., the 28 day strength of 55 MPa for flowable consistency was obtained at a water addition of 3.6 litres of water per 20kg bag of Conbextra C.

Description

General purpose shrinkage compensated cementitious grout, is supplied as a ready to use dry powder. The addition of a controlled amount of clean water produces a flowing shrinkage compensated grout for gap thicknesses from 10mm up to 100mm.

Conbextra C is a blend of Portland cement, specially graded fillers and additives which impart controlled expansion in the plastic and hardened state whilst minimising water demand. The low water demand ensures high early strength. The graded filler is designed to assist uniform mixing and produce a consistent, flowable grout.

Maximum aggregate size for pumping is 0.3mm.

In applications where the maximum flow properties and flow retention times are required, **Conbextra HF** should be considered.

Standards Compliance

AS 1478.2-2005 Appendix E : Test for Early Volume Change.

AS 1478.2-2005 Table 4.1.2.2 : Test for Consistency.

Fosroc® Conbextra® C

Test Results to ASTM Specification C1107: 2001

| Test Method | Standard | Result | |
|------------------------|-----------------|--------------------|------------------------|
| Flow Consistency | ASTM C1437:2007 | 126% | |
| Setting Time | ASTM C191:2008 | Initial: Final: | 4.8 hours 6.0 hours |
| Plastic Volume Change | ASTM C827:2010 | +0.57% | |
| Hardened Volume Change | ASTM C1090:2010 | 1 day | 0.18% |
| | | 3 days | 0.18% |
| | | 14 days | 0.21% |
| | | 28 days | 0.24% |
| | | 56 days | 0.22% |
| Compressive Strength | ASTM C109:2011b | 1 day | 30.7 MPa |
| | | 3 days | 49.7 MPa |
| | | 7 days | 57.8 MPa |
| | | 28 days | 64.0 MPa |

Note: All tests were carried out at 25°C ± 2°C until the age of the test. All above test results are independent third party results. Copies of these test results are available on request. The tests were carried out at a water addition rate of 3.6L per 20kg.

Application Instructions

Preparation

Foundation surface

The substrate surface must be free from oil, grease or any loosely adhered material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris. These may need to be grouted beforehand.

Pre-soaking

Several hours prior to grouting, the area of cleaned foundation should be flooded with fresh water. Immediately before grouting takes place, any free water should be removed with particular care being taken to blow out all bolt holes and pockets.

Base plate

It is essential that this is clean and free from oil, grease, scale, paint or coating of any kind. Air pressure relief holes should be provided to allow venting of any isolated high spots.

Levelling shims

If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

Formwork

The formwork should be constructed to be leakproof. This can be achieved by using foam rubber strip or construction silicone sealant beneath the constructed formwork and between joints.

In some cases it is practical to use a sacrificial semi-dry sand and cement formwork.

The formwork should include outlets for pre-soaking.

Generally the gap width between the perimeter formwork and the plate edge should not exceed 150mm on the pouring side and 50mm on the opposite side. It is advisable where practical to have no gap at the flank sides.

Mixing

A forced-action mixer is essential. Mix for 3 to 5 minutes at a slow speed (400/500rpm) in a suitably sized drum using appropriate equipment such as the Ransom MDR59 140 x 600 M14 Helical mixing paddle (product code: N4020892-UNIT) fitted to a heavy-duty 1600W mixer, such as Ransom RAN160 (product code: NP7AN160-UNIT) or equivalent.

The selected water content should be accurately measured into the mixing bucket. While mixing, slowly add the total contents of the **Conbextra C** bag, mix continuously for 5 minutes, ensuring a smooth, even consistency is obtained. Always add the powder to the water.

| Required Consistency | Litres of water added per 20kg bag | Yield - litres of mixed material |
|----------------------|------------------------------------|----------------------------------|
| Stiff | 2.6 - 3.4 | 10.4 |
| Plastic | 3.4 - 3.6 | 10.7 |
| Flowable | 3.6 - 3.9 | 10.8 |

Mixing larger volumes

Larger quantities will require a high shear vane mixer. Do not use a colloidal impeller mixer.

To enable the grouting operation to be carried out continuously, it is essential that sufficient mixing capacity and labour are available. The use of a grout holding tank with provision to gently agitate the grout may be required.

Fosroc® Conbextra® C

Mixing part bags

It is recommended that full bags be mixed, however for applications where smaller quantities of product are required, experienced applicators may elect to mix half bags by weighing out (the correct quantity of product) and mixing with half the recommended quantity of water. In doing so the contractor accepts the risk of any off-ratio mixing. Agitate the dry product before weighing out to minimise any segregation. Reliable scales should be used to weigh out individual components.

Placing

At 23°C place the grout within 20 minutes of mixing to gain full benefit of the expansion process.

Conbextra C can be placed in thicknesses from 10mm up to 100mm in a single pour when used as an underplate grout. Where the grouting gap beneath the base plate exceeds the maximum thickness allowed, then the grout can filled / bulked out with **Conbextra Grout Aggregate*** to minimise exotherm heat build up. Alternatively **Conbextra Deep Pour** is available for pours up to 500mm thick.

Filling/bulking out of the grout should not exceed a ratio of 2:1 (grout:aggregate by weight). Please refer to the **Conbextra Grout Aggregate** TDS for more guidance on bulking out of cement based grouts.

Any bolt pockets must be grouted prior to grouting between the substrate and the base plate.

Continuous grout flow is essential. Sufficient grout must be prepared before starting. The time taken to pour a batch must be regulated to the time to prepare the next one.

Pouring should be from one side of the void to eliminate any air or pre-soaking water becoming trapped under the baseplate. It is advisable to pour the grout across the shortest distance of travel. The grout head must be maintained at all times so that a continuous grout front is achieved.

Flow properties of mixed grout

The flow distances given below in (mm) are intended as a guide. Actual flow distances will vary depending on site conditions:

| Gap Depth (mm) | Flowable 100mm head (mm) | Flowable 250mm head (mm) |
|----------------|--------------------------|--------------------------|
| 10 | 320 | 1080 |
| 20 | 850 | 2300 |
| 30 | 1350 | 2700 |
| 40 | 2000 | 2700+ |
| 50 | 2700 | 2700+ |

Pumping

Where large volumes have to be placed **Conbextra C** may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps may also be suitable. Maximum aggregate size for pumping is 0.3mm. Ensure the selected pump is capable of pumping this size aggregate.

Curing

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of **Concure** curing membrane or continuous application of water and/or wet hessian.

Cleaning

Conbextra C should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically.

Limitations

Low temperature working

When the air or contact surface temperatures are 5°C or below on a falling thermometer, grouting should be postponed.

For ambient temperatures below 10°C the formwork should be kept in place for at least 36 hours.

Normal precautions for winter working with cementitious materials should then be adopted.

High temperature working

At ambient temperatures above 35°C cool water (below 20°C) should be used for mixing the grout prior to placement.

Supply

Conbextra C 20kg: FC501040-20KG

Yield

| Consistency (AS 1478.2-2005 Table 4.1.2.2) | Yield (Litres of mixed material) |
|--|----------------------------------|
| Stiff | 10.4 |
| Plastic | 10.7 |
| Flowable | 10.8 |

Storage

Conbextra C has a shelf life of 36 months from date of manufacture if kept in the original, unopened bags. Refer to the manufacture date indicated on the packaging. Do not use if there are lumps in the product, or a loss of workability (requiring more water to be added) is experienced.

Fosroc® Conbextra® C

Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



constructive solutions

*Manufactured and sold under license from Fosroc International Limited. Fosroc, Conbextra and the Fosroc logo are trade marks of Fosroc International Limited, used under license. .

Parchem Construction Supplies Pty Ltd

7 Lucca Road, Wyong NSW 2259

Ph: 1800 812 864

www.fosroc.com.au

ABN 80 069 961 968

Distributed in New Zealand by: Concrete Plus Ltd

150 Hutt Park Road Gracefield Ph: 0800 657 156

www.fosroc.co.nz

NZBN 9429033691282