

## High flow, high ultimate strength, dual shrinkage compensated, precision cementitious grout

### Uses

Heavy duty precision grouting of gaps from 10mm to 125mm, where high flow and high ultimate strength is required. Applications include grouting of:

- Baseplates and soleplates of large machines subject to moderate dynamic loads
- Crane rail soleplates, beams, columns and structural building members

### Advantages

- Non-metallic dual expansion system compensates for shrinkage in both the plastic and hardened states
- Excellent initial flow and flow retention suitable for large and small grout pours
- Rapid strength gain facilitates efficient installation and operation of plant
- High ultimate strength and low permeability ensure durability of the hardened grout
- Hydrogen-free gaseous expansion
- Chloride free
- Suitable for pumping or pouring over a large range of application consistencies and temperatures

### Properties

Test Method	Standard	Result							
Compressive Strength	AS 1478.2:2005 Tested at 23°C	Consistency	Water Addition	8 hrs MPa	12 hrs MPa	1 Day MPa	7 Days MPa	28 Days MPa	56 Days MPa
		Flowable	2.7L	5	20	55	80	100	105
		Fluid	3.0L	-	13	40	70	85	90
	AS 1478.2:2005 Tested at 30°C	Consistency	Water Addition	8 hrs MPa	12 hrs MPa	1 Day MPa	7 Days MPa	28 Days MPa	56 Days MPa
		Flowable	2.7L	26	40	60	90	100	105
		Fluid	3.0L	20	30	50	80	85	90
Flexural Strength (Modulus of Rupture)	AS 1012.11 - 2000	1 Day	5.8 MPa						
		7 Days	11.4 MPa						
		28 Days	13.7 MPa						
Indirect Tensile Strength	AS 1012.10.2000	1 Day	3.6 MPa						
		7 Days	5.1 MPa						
		28 Days	7.0 MPa						
Setting Time	AS 1012.18:1996	2.5 hours - initial set 5.0 hours - final set							
Fresh Wet Density		2315 kg/m <sup>3</sup> - depending on consistency used							
Alkali reactive particles	Rapid Mortar Bar Test (RTA T363)	Non-reactive							

### Standards Compliance

AS1478.2-2005 Appendix E test for early volume change

AS1478.2.2005 (table 4.1.2.2) for workability.

### Description

**Conbextra HS**, shrinkage compensated ultra high-strength cementitious precision grout, is supplied as a ready to use dry powder. The addition of a controlled amount of clean water produces a free-flowing precision grout for gap thicknesses 10mm to 125mm. In addition the low water requirement ensures high early strength and long term durability.

**Conbextra HS** is a blend of portland cements, graded fillers and chemical additives which impart controlled expansion in both the plastic and hardened states. The filler grading minimises segregation and bleeding over a wide range of application consistencies.

Maximum aggregate size for pumping is 1.0mm.

# Fosroc® Conbextra® HS

<b>Flow Characteristics</b>	AS 1478.2:2005	600mm (Flow Trough)
<b>Expansion Characteristics</b>	AS1478.2-2005 ASTM C1107-91	An expansion of up to 2% overcomes plastic settlement Conforms to expansion in hardened state for drying shrinkage
<b>Minimum Thickness</b>		10mm
<b>Maximum Thickness</b>		125mm

Clarification of property values: The typical properties given above are derived from laboratory testing. Compressive strengths stated above were measured using cube samples. Test results obtained will vary if carried out to an alternative standard or sample dimensions are used. Note: Compressive strengths stated were measured at bottom end water addition.

## Flow characteristics of mixed grout

The flow distances given below in (mm) are intended as a guide. Actual flow distances will vary depending on site conditions:

Gap Depth (mm)	Flowable 100mm head (mm)	Flowable 250mm head (mm)	Fluid 100mm head (mm)	Fluid 250mm head (mm)
10	360	1200	900	2500
20	950	2600	1900	3000
30	1500	3000	3000	3000+

## Preparation

### Foundation surface

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut back to a sound base. Bolt holes or fixing pockets must be blown clean of any dirt or debris. These may need to be grouted beforehand.

### Pre-soaking

Several hours prior to grouting, the area of cleaned foundation should be flooded with fresh water. Immediately before grouting takes place, any free water should be removed. Particular care should be taken to blow out all bolt holes and pockets.

### Base plate / grout interface

It is essential that this is clean and free from oil, grease, scale, paint or coating of any kind. Air pressure relief holes should be provided to allow venting of any isolated high spots.

### Levelling shims

If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

### Formwork

The formwork should be constructed to be leakproof as **Conbextra HS** is a free flowing grout. This can be achieved by using foam rubber strip or Construction Silicone\* beneath the constructed formwork and between joints.

The formwork should include outlets for the pre-soaking water.

The unrestrained surface area of the grout must be kept to a minimum. Generally the gap width between the perimeter formwork and the plate edge should not exceed 150mm on the pouring side and 50mm on the opposite side. There should be no gap at the flank sides.

### Mixing

A forced-action mixer is essential. Mix for 3 to 5 minutes at a slow speed (400/500 rpm) in a suitably sized drum using appropriate equipment such as the Ransom MDR59 140 x 600 M14 Helical mixing paddle (product code: N4020892-UNIT) fitted to a heavy-duty 1600W mixer, such as Ransom RAN160 (product code: NP7AN160-UNIT ) or equivalent.

The selected water content should be accurately measured into the mixing bucket. While mixing, slowly add the total contents of the **Conbextra HS** bag, mix continuously for 5 minutes, ensuring a smooth, even consistency is obtained. Always add the powder to the water.

Required Consistency	Litres of water added per 20kg bag	Yield - litres of mixed material
Flowable	2.7	9.8
Fluid	3.0	10.1

### Mixing larger volumes

Larger quantities will require a high shear vane mixer. Do not use a colloidal impeller mixer.

It is essential that machine mixing capacity and labour availability is adequate to enable grouting operation to be

# Fosroc®

## Conbextra® HS

carried out continuously. This may require the use of a holding tank with provision for gentle agitation to maintain fluidity.

The selected water content should be accurately measured into the mixer. Slowly add the total contents of the **Conbextra HS** bags, mix continuously for 5 minutes, ensuring a smooth, even consistency is obtained.

### Placing

Place the grout within 15 minutes of mixing to gain the full benefit of the expansion process.

**Conbextra HS** can be placed in thicknesses up to 125mm in a single pour. Any bolt pockets must be grouted prior to grouting between the substrate and the base plate. Continuous grout flow is essential.

Where grout gap depth is in excess of 125mm up to 500mm, **Conbextra Deep Pour** should be considered or the **Conbextra HS** bulked out with **Conbextra Grout Aggregate**.

Filling/bulking out of the grout should not exceed a ratio of 2:1 (Grout:Aggregate w/w). Please refer to the **Conbextra Grout Aggregate** TDS for more guidance on bulking out of cement based grouts.

**Removable hopper:** For larger pours the grout may be hand placed or pumped into a removable hopper (trough).

Sufficient grout must be available prior to starting and the time taken to pour a batch must be regulated to the time taken to prepare the next one. Continual grout pour must be ensured.

The mixed grout should be poured only from one side of the void to eliminate the entrapment of air or surplus pre-soaking water. This is best achieved by pouring the grout across the shortest distance of travel. The grout head must be maintained at all times so that a continuous grout front is achieved.

### Pumping

Where large volumes have to be placed **Conbextra HS** may be pumped. A heavy duty diaphragm pump is recommended for this purpose. Screw feed and piston pumps may also be suitable. Maximum aggregate is 1.0mm. Ensure the selected pump is capable of pumping this size aggregate.

### Curing

On completion of the grouting operation, exposed areas should be thoroughly cured. This should be done by the use of **Concure** curing membrane, continuous application of water and/or wet hessian.

### Important notice

A Safety Data Sheet (SDS) is available from the Fosroc website. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

### Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



constructive solutions

\*Manufactured and sold under license from Fosroc International Limited. Fosroc, Conbextra and the Fosroc logo are trade marks of Fosroc International Limited, used under license.

### Cleaning

**Conbextra HS** should be removed from tools and equipment with clean water immediately after use. Cured material can be removed mechanically.

### Limitations

#### Low temperature working

When the air or contact surface temperatures are 5°C or below on a falling thermometer, warm water (30-40°C) is recommended to accelerate strength development.

For ambient temperatures below 10°C the grout consistency should be flowable and the formwork should be maintained in place for at least 36 hours.

Normal precautions for winter working with cementitious materials should then be adopted.

#### High temperature working

At ambient temperatures above 35°C the mixed grout should be stored in the shade. Cool water (below 20°C) should be used for mixing the grout.

### Supply

<b>Conbextra HS 20kg:</b>	FC502000-20KG
---------------------------	---------------

### Yield

Allowance should be made for wastage when estimating quantities required. The approximate yield for different consistencies is:

#### Yield per 20kg bag mixed

Flowable consistency	9.8 litres
Fluid consistency	10.1 litres

### Storage

**Conbextra HS** has a shelf life of 36 months from date of manufacture if kept in the original, unopened bags. Refer to the manufacture date indicated on the packaging. Do not use if there are lumps in the product, or a loss of workability (requiring more water to be added) is experienced.

**Parchem Construction Supplies Pty Ltd**

7 Lucca Road, Wyong NSW 2259

Ph: 1800 812 864

www.fosroc.com.au

ABN 80 069 961 968

**Distributed in New Zealand by: Concrete Plus Ltd**

150 Hutt Park Road Gracefield Ph: 0800 657 156

www.fosroc.co.nz

NZBN 9429033691282