

# Technical Data

## Dimetcote 15 Slurry



### Product description

Dimetcote 15 Slurry is a two-pack, zinc-rich ethyl silicate based coating that complies with the compositional requirements for SSPC Paint 20 level 1 and the zinc pigment complies with the requirements of ASTM D520 Type II. Dimetcote 15 Slurry complies with AS/NZS 3750.15 - Type 4.

---

### Recommended use

A general purpose, heavy duty, anti-corrosive primer:

1. As the first coat in a multiple layer system.
  2. As a single coating for long term protection of steel exposed to moderately to severely corrosive environment. Resistant to cyclic dry temperatures up to 400°C.
- 

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry ( $\mu\text{m}$ )	50	150	75
Film thickness, wet ( $\mu\text{m}$ )	90	270	135
Theoretical spreading rate ( $\text{m}^2/\text{l}$ )	11	3,7	7,3

### Comments

There is a risk of mud-cracking if the thickness exceeds 120  $\mu\text{m}$ .

---

### Approvals

APAS approved to specification 2908.

---

## Physical properties

<b>Colour</b>	Grey
<b>Solids (vol %)*</b>	55 ± 2
<b>Flash point</b>	15°C ± 2 (Setaflash)
<b>VOC</b>	585 gms/ltr UK-PG6/23(97). Appendix 3
<b>Gloss</b>	Flat
<b>Water resistance</b>	Very good
<b>Abrasion resistance</b>	Excellent
<b>Solvent resistance</b>	Excellent
<b>Chemical resistance</b>	Excellent within pH-range 6-10
<b>Flexibility</b>	Limited

\*Measured according to ISO 3233:1998 (E)

---

## Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

### Bare steel

Cleanliness: Blast cleaning to Sa 2½ (ISO 8501-1:2007). Roughness: using abrasives suitable to achieve grade Fine to Medium G (30-85 µm, Ry5) (ISO 8503-2)

### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be min. 5°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Zinc silicate paints in general requires moisture for curing. At low humidity the curing will be improved by gently sprinkling fresh water over the paint film, and/or by artificial humidification of the surrounding atmosphere. The paint must be completely cured before topcoating, otherwise the adhesion of the subsequent coat will be unsatisfactory. Use Methyl ethyl ketone (MEK) test according to ASTM D 4752-87 to verify the curing time before topcoating. Unweathered zinc silicate films are porous and the porosity may vary according to the weather condition during application and the application technique. When overcoating, the air in the pores will escape through the new coat of paint and may cause blisters or pinholes ("popping") in the coat just after application. To avoid this a mist coat/full coat technique is recommended:

First apply a thin coat to fill the pores in the zinc silicate film and a few minutes later apply to full specified film thickness. In difficult cases it may be necessary to thin the next coat, or use Penguard Tie Coat 100 as first overcoat.

---

## Application methods

<b>Spray</b>	Use airless spray or conventional spray
<b>Brush</b>	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness. In order to avoid settling of heavy zinc, continuous mechanical stirring during application is recommended.

---

## Application data

<b>Mixing ratio (volume)</b>	3:1
<b>Mixing</b>	3 parts Comp. A to 1 part Dimetcote 15/18 Slurry, Comp. B by volume.
<b>Pot life (23°C)</b>	8 hours. (Reduced at higher temp.)
<b>Thinner/Cleaner</b>	Jotun Thinner No. 4/25. Adjusting spray pattern and drying may sometimes become necessary. Use max 5% *, Jotun Thinner No. 4 (fast evaporation) when temperature is low and Jotun Thinner No. 25 (slow evaporation) when temperature is high.
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	10 MPa (100 kp/cm <sup>2</sup> , 1400 psi)
<b>Nozzle tip</b>	0.46-0.58 mm (0.018-0.023")
<b>Spray angle</b>	40-80°
<b>Filter</b>	Check to ensure that filters are clean.
<b>Note</b>	* Thinner should be added after mixing components. Spray: Specially developed equipment for zinc rich coatings is available from most equipment suppliers.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate
- \* Relative humidity at 70%

<b>Substrate temperature</b>	<b>5°C</b>	<b>10°C</b>	<b>23°C</b>	<b>40°C</b>
<b>Surface dry</b>	90 min	60 min	30 min	10 min
<b>Through dry</b>	3 h	90 min	60	25 min
<b>Cured <sup>1</sup></b>	72 h	48 h	24 h	10 h
<b>Dry to recoat, minimum <sup>2</sup></b>	72 h	48 h	24 h	10 h
<b>Dry to recoat, maximum <sup>3</sup></b>				

1. Curing time to be verified by MEK test (ASTM D 4752-87)
1. Recommended data given for recoating with coatings normally specified on top of zinc ethyl silicate coatings.
2. The surface should be free of zinc salts and other contamination prior to application.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

<b>Dimetcote 15 Slurry</b>	<b>1 x 75 µm</b>	<b>(Dry Film Thickness)</b>
Penguard HB	1 x 125 µm	(Dry Film Thickness)
Jotacote 371	1 x 75 µm	(Dry Film Thickness)

As an economical potable water tank lining:

**Dimetcote 15 Slurry**  
Jotaprime 505  
Other systems may be specified, depending on area of use

**1 x 75 µm**  
1 x 50 µm

**(Dry Film Thickness)**  
(Dry Film Thickness)

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed. The component A is a zinc dust slurry and settling may occur during storage. The component B must be stored below 25°C. SHELF LIFE: 2 years at 23°C for Comp. A., 12 months for Comp. B, subject to re-inspection thereafter. Higher temperatures during storage may reduce the shelf life and may lead to gelling in the tin.

---

## Handling

Handle with care. Stir well before use. Continuous stirring during application will prevent the heavy zinc pigment from settling.

---

## Packing size

10 litre unit: 7.5 litres Comp. A (zinc slurry) in a 10 litre container and 2.5 litres Dimetcote 15/18 Slurry, Comp. B. (liquid) in a 2.5 litre container.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

## DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 3 MARCH 2011 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED