

# Geogrid

## Secugrid® Q (PP)



Global Synthetics



0799 - CPD-20

NAUE GmbH & Co. KG  
Gewerbstrasse 2  
32339 Espelkamp-Fiestel, Germany

Phone: +49 5743 41-0 · Fax: +49 5743 41-240  
E-Mail: info@naue.com · Internet: www.naue.com

[www.globalsynthetics.com.au](http://www.globalsynthetics.com.au)

Sydney 8/28 Dramzi Rd, Girraween, NSW 2145  
Phone: 02 9631 0744 · Fax 02 9631 0755

Australian Company – Global Expertise

Brisbane 44 Telford St, Virginia, QLD 4014  
Phone: 07 3865 7000 · Fax 07 3865 4444

[info@globalsynthetics.com.au](mailto:info@globalsynthetics.com.au)

Perth 17 Church Rd, Maddington, WA 6109  
Phone: 08 9459 4300 · Fax 08 9459 4311

### Product description:

Laid geogrid made of stretched, monolithic polypropylene (PP) flat bars with welded junctions used for the reinforcement in many fields of civil engineering including landfill engineering, road construction and hydraulic engineering

Property	Test method*	Unit	20/20 Q1	30/30 Q1	40/40 Q1
Raw material	-	-	polypropylene (PP), white		
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	155	200	240
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 20 / ≥ 20	≥ 30 / ≥ 30	≥ 40 / ≥ 40
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 8 / ≤ 8		
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	8 / 8	12 / 12	16 / 16
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	16 / 16	24 / 24	32 / 32
Aperture size, md x cmd**	-	mm x mm	approx. 33 x 33	approx. 32 x 32	approx. 31 x 31
UV-resistance (remaining tensile strength)	EN 12224	%	95.0		
Weather resistance	FGSV	class	high		
Production specific elongation	-	%	0		
Roll dimensions, width x length	-	m x m	4.75 x 100		

\*based on, \*\*md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.