

# DUREBILD<sup>®</sup> STE MIO

Surface Tolerant Micaceous Iron Oxide Epoxy Coating

**PC 565**

- FEATURES**
- SUPERIOR SURFACE WETTING PROPERTIES AND CORROSION RESISTANCE
  - HIGH PERFORMANCE MIO COATING FOR NEW OR EXISTING STEEL
  - IDEAL MAINTENANCE COATING OVER MOST WELL ADHERED AGED COATINGS
  - MIO PIGMENTATION PROVIDES IMPROVED WEATHERABILITY PROPERTIES
  - EXCELLENT MOISTURE RESISTANCE
  - SELF PRIMING FINISH

**USES** DUREBILD<sup>®</sup> STE MIO has been developed specifically for Australasian conditions using the latest epoxy technology. It is principally used as a high-performance maintenance coating over hand, power tool or high-pressure water cleaned surfaces where blasting is impractical or not allowed. This coating can also be used for new work and where required as an intermediate coat. DUREBILD<sup>™</sup> STE MIO is ideal for fresh and salt-water immersion over abrasive blast cleaned steel. It provides excellent protection against the splash and spillage of a wide range of chemicals. DUREBILD<sup>®</sup> STE MIO can be topcoated with a wide range of coating types and is available with a cold cure hardener that is bloom free.

**SPECIFICATIONS** Approved to APAS 2977  
AS 3750.1

## RESISTANCE GUIDE

<b>HEAT RESISTANCE</b>	Up to 120°C dry heat.	<b>ALKALIS</b>	Suitable for splash and spillage of strong alkalis. Aluminium containing colours are not recommended for alkaline conditions.
<b>WEATHERABILITY</b>	Epoxy coatings may yellow with time. On exterior exposure some chalking may also occur. This will not detract from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	<b>SALTS</b>	Excellent resistance to neutral and alkali salts. Aluminium containing colours are not recommended for alkaline conditions.
<b>SOLVENTS</b>	Resists splash and spillage of most hydrocarbon solvents, refined petroleum products and most common alcohols.	<b>WATER</b>	Excellent resistance to immersion in fresh and salt water. Aluminium containing colours are not recommended for immersion conditions.
<b>ACIDS</b>	Suitable for splash and spillage of mild acids. Aluminium containing colours are not recommended for acidic conditions.	<b>ABRASION</b>	Good when fully cured.

## TYPICAL PROPERTIES AND APPLICATION DATA

<b>CLASSIFICATION</b>	Surface Tolerant Epoxy MIO	<b>APPLICATION CONDITIONS</b>			
<b>FINISH</b>	Semi Gloss		<b>REFER TO PAGE 2</b>		
<b>COLOUR</b>	Natural Grey, Mid Grey Pipeline Grey (MTO) and St Enoch Grey (MTO)				
<b>COMPONENTS</b>	Two				
<b>SOLIDS BY VOLUME</b>	Refer to Page 2				
<b>VOC LEVEL</b>	Refer to Page 2				
<b>FLASH POINT</b>	40°C				
<b>POT LIFE (4L, 25°C)</b>	Refer to Page 2				
<b>MIXING RATIO (V/V)</b>	Part A : 4      Part B : 1				
<b>THINNER</b>	920-08925      Dulux <sup>®</sup> Epoxy Thinner				
<b>PRODUCT CODE</b>	775-00805      Natural Grey 775-63006      Mid Grey 775-89962      Pipeline Grey (MTO) 775-00806      St Enoch Grey (MTO) 976-84539      Standard Hardener 976-84685      Cold Cure Hardener	<b>SUITABLE SUBSTRATES</b>	Prepared rusty steel. Aged tightly adhering coatings. Prepared concrete, aluminium and galvanised steel.		
		<b>APPLICATION METHODS</b>	Brush, roller, conventional or airless spray.		

# DUREBILD® STE MIO

Standard Hardener						
<b>COATING THICKNESS</b>			<b>APPLICATION CONDITIONS</b>			
	Min	Max	Recom.	Min	Max	
Wet film per coat (microns)	120	250	150	Air Temperature	10°C	45°C
Dry film per coat (microns)	100	210	125	Substrate Surface Temperature	10°C	45°C
				Relative Humidity		85%
<b>SOLIDS BY VOLUME</b>	84% (Natural Grey)			<b>POT LIFE</b>	60 Minutes (4L, 25°C)	
<b>VOC LEVEL</b>	<220 g/L (Natural Grey)					
<b>Drying characteristics at 125 microns dry film thickness</b>						
<b>Temperature</b>	<b>Humidity</b>	<b>Touch</b>	<b>Handle</b>	<b>Full Cure</b>	<b>Overcoat</b>	<b>Max*</b>
10° C	50%	14 Hours	36 Hours	7 Days	36 Hours	4 Weeks
15° C	50%	10 Hours	24 Hours	7 Days	24 Hours	4 Weeks
25° C	50%	6 Hours	14 Hours	7 Days	14 Hours	4 Weeks
<b>TYPICAL SPREADING RATE AT RECOMMENDED DRY FILM BUILD</b>				A spreading rate of 6.7 sq. metres per litre corresponds to 125 microns dry film thickness assuming no losses. Practical spreading rates will vary depending on such factors as method and conditions of application and surface roughness.		

Cold Cure Hardener						
<b>COATING THICKNESS</b>			<b>APPLICATION CONDITIONS</b>			
	Min	Max	Recom.	Min	Max	
Wet film per coat (microns)	120	250	150	Air Temperature	5°C	45°C
Dry film per coat (microns)	100	210	125	Substrate Surface Temperature	5°C	45°C
				Relative Humidity		85%
<b>SOLIDS BY VOLUME</b>	84% (Natural Grey)			<b>POT LIFE</b>	60 Minutes (4L, 25°C)	
<b>VOC LEVEL</b>	<210 g/L (Natural Grey)					
<b>Drying characteristics at 125 microns dry film thickness</b>						
<b>Temperature</b>	<b>Humidity</b>	<b>Touch</b>	<b>Handle</b>	<b>Full Cure</b>	<b>Overcoat</b>	<b>Max</b>
5° C	50%	14 Hours	28 Hours	7 Days	28 Hours	4 Weeks
10° C	50%	13 Hours	24 Hours	7 Days	24 Hours	4 Weeks
15° C	50%	12 Hours	18 Hours	7 Days	18 Hours	4 Weeks
25° C	50%	6 Hours	9 Hours	7 Days	9 Hours	4 Weeks
<b>TYPICAL SPREADING RATE AT RECOMMENDED DRY FILM BUILD</b>				A spreading rate of 6.7 sq. metres per litre corresponds to 125 microns dry film thickness assuming no losses. Practical spreading rates will vary depending on such factors as method and conditions of application and surface roughness.		

These figures are given as a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level.

\* When used for non-immersion conditions. Refer to PRECAUTIONS section for overcoating intervals and requirements for immersion service.

## TYPICAL SYSTEMS

(The typical systems are offered as a guide only and are not to be used as a specification. It is recommended that the specific needs of a project be discussed with a Dulux Protective Coatings Consultant.)

SURFACE	PREPARATION GUIDE	SYSTEM		DRY FILM THICKNESS
STEEL Maintenance	Hand or Power tool clean AS1627.2 St 3 Abrasive blast AS1627.4 Class 1	1st Coat	DUREBILD® STE MIO	125 Microns
		2nd Coat	DUREBILD® STE MIO	125 Microns
		Spot Prime	DUREBILD® STE MIO	125 Microns
		1st Coat	DUREBILD® STE MIO	125 Microns
		2nd Coat	WEATHERMAX™ HBR	100 Microns
STEEL Immersion -Salt or Freshwater	Abrasive blast to AS1627.4 Class 3.0	1st Coat	DUREBILD® STE MIO	125 - 200 Microns
		2nd Coat	DUREBILD® STE MIO	125 - 200 Microns
ALUMINIUM	Clean, degrease and abrade surface by whip blasting.	1st Coat	DUREBILD® STE MIO	125 - 200 Microns

# DUREBILD® STE MIO

<b>SURFACE PREPARATION</b>	Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Rust millscale, oxide deposits and old paint films on metal surfaces should be removed by hand or power tool (AS1627.2 St 3) cleaning as a minimum. Coating performance is proportional to the degree of surface preparation and abrasive blast cleaning to a minimum AS1627.4 Class 2 is preferred for more severe environments. Immersed steel must be prepared to AS1627.4 Class 3
<b>APPLICATION</b>	Stir each can thoroughly until the contents are uniform. Use of a power mixer is recommended. Mix the contents of both packs together thoroughly using a power mixer and allow to stand for 10 minutes. Remix thoroughly before using and continue mixing during application.
<b>BRUSH/ROLLER</b>	Apply even coats of the mixed material to the prepared surface. When brushing and rolling additional coats may be required to attain the specified thickness.
<b>CONVENTIONAL SPRAY</b>	Thinning is not normally required, however a small amount (5% or less by volume) of Dulux® Epoxy Thinner (920-08925) can be added. Ensure paint is regularly agitated during application to prevent separation. <u>Typical Set-up</u> Graco Delta Gun: 1.8mm (239543) Pressure at Pot: 65-100 kPa (10-15 p.s.i.) Pressure at Gun: 385-420 kPa (55-60 p.s.i.)
<b>AIRLESS SPRAY</b>	Standard airless spray equipment such as a Graco 45:1 or 56:1 Xtreme with a fluid tip of 17-21 thou (0.43-0.53mm) and an air supply capable of delivering 550-690 kPa (80 -100 psi) at the pump. Thinning is not normally required but up to 50ml/litre of Dulux® Epoxy Thinner (920-08925) may be added to ease application. Ensure paint is regularly agitated during application to prevent separation.
<b>PRECAUTIONS</b>	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Freshly mixed material must not be added to material that has been mixed for some time. Do not apply at temperatures below 10°C when using standard hardener or below 5°C when using Cold Cure hardener. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. When used for immersion conditions the maximum overcoat interval is 3 days at 25°C. The coating MUST be fully cured and solvent free prior to being placed under immersion conditions. For best results in water immersion conditions replace Dulux® Epoxy Thinner (920-08925) with Dulux® CR Reducer (965-63020). Aluminium containing colours are not recommended for acidic and alkaline conditions. Do NOT use Cold Cure hardener in immersion conditions. This product is not a decorative coating, and colour variations will occur due to different application techniques. Coatings containing micaceous iron oxide are prone to marring but this will not affect the protective properties. Do not use as a primer over galvanised steel when using Cold Cure hardener as delamination can occur. Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level.
<b>CLEAN UP</b>	Clean all equipment with Dulux® Epoxy Thinner (920-08925) immediately after use.
<b>OVERCOATING</b>	Aged coating should be tested for lifting by a method appropriate for the coating thickness, for example 'X' cut or cross-hatch methods. If it lifts, remove it. The surface must be free of oil, grease and other contaminants. High-pressure water wash at 8.3 to 10.3 MPa (1,200 - 1,500 p.s.i.) to remove loosely adhering chalk and dust. Abrasion may be required depending on surface condition. If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.
<b>SAFETY PRECAUTIONS</b>	<b>Read Data Sheet, Material Safety Data Sheet and any precautionary labels on containers.</b>
<b>STORAGE</b>	Store as required for a flammable liquid Class 3 in a bonded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
<b>HANDLING</b>	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
<b>USING</b>	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spray painting, users should comply with the provisions of the respective State Spray Painting Regulations.
<b>FLAMMABILITY</b>	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO <sub>2</sub> or dry chemical powder. On burning will emit toxic fumes.
<b>WELDING</b>	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

**MATERIAL SAFETY DATA SHEET is available from Customer Service (132377) or [www.duluxprotectivecoatings.com.au](http://www.duluxprotectivecoatings.com.au)**

Dulux Protective Coatings a division of DuluxGroup (Australia) Pty Ltd  
1956 Dandenong Road, Clayton 3168  
A.B.N. 67 000 049 427  
Dulux, Durebild and Weathermax are registered trademarks. DuluxGroup is a trademark.

PACKAGING	Available in 15 litre pack
TRANSPORTATION WEIGHT	1.73 kg/litre (Average of components)
DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 8.3 UN 2734

Any advice, recommendation, information, assistance or service provided by DULUX Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in coastal areas and for large projects to ensure proper performance.