

# FERREKO<sup>®</sup> No 5

Water Borne Micaceous Iron Oxide Acrylic Finish

PC 570

- FEATURES**
- WATER BORNE – EASY CLEAN UP AND NO STRONG SOLVENT ODOUR
  - USE OVER INORGANIC ZINC RICH PRIMERS WITHOUT MIST COATING
  - EXCELLENT UV DURABILITY IN COASTAL OR SALT ENVIRONMENT

**USES** FERREKO<sup>®</sup> No 5 is a one-pack acrylic resin-micaceous iron oxide finish with excellent durability particularly as a topcoat system over zinc rich primers. The pigment interlocks in the film to reduce moisture permeability and improve resistance to degradation by UV light.  
FERREKO<sup>®</sup> No 5 is recommended on structural steelwork, wharf facilities, cranes, tanks and exposed pipelines and industrial plant in all applications not subject to high physical abrasion.

**SPECIFICATIONS** AS/NZS 3750.16

## RESISTANCE GUIDE

<b>HEAT RESISTANCE</b>	Up to 90°C dry heat.	<b>ALKALIS</b>	Suitable for splash and spillage of mild alkali. Aluminium containing colours are not recommended for alkaline conditions.
<b>WEATHERABILITY</b>	Excellent gloss and colour retention on exterior exposure.	<b>SALTS</b>	Unaffected by splash and spillage of salt solutions. Aluminium containing colours are not recommended for alkaline conditions.
<b>SOLVENTS</b>	Fair. Not recommended for areas subject to splash and spillage.	<b>WATER</b>	Withstands rain and condensation for prolonged periods.
<b>ACIDS</b>	Suitable for splash and spillage exposure to weak solutions of inorganic acids. Aluminium containing colours are not recommended for acidic conditions.	<b>ABRASION</b>	Good for single pack coating.

## TYPICAL PROPERTIES AND APPLICATION DATA

<b>CLASSIFICATION</b>	Micaceous iron oxide Acrylic	<b>APPLICATION CONDITIONS</b>	Min	Max	
<b>FINISH</b>	Low metallic lustre	Air Temperature	10°C	45°C	
<b>COLOUR</b>	MTO Only - Structural Green, St Enoch Grey and Mid Grey	Substrate Surface Temperature	10°C	45°C	
		Relative Humidity		85%	
<b>COMPONENTS</b>	One		Min	Max	Recom.
<b>SOLIDS BY VOLUME</b>	45% (Structural Green)	Wet film per coat (microns)	90	135	110
<b>VOC LEVEL</b>	<80 g/L (Structural Green)	Dry film per coat (microns)	40	60	50
<b>FLASH POINT</b>	Non flammable	<b>SUITABLE SUBSTRATES</b>	Suitably primed steel, prepared concrete, aluminium and galvanised steel.		
<b>POT LIFE</b>	Not applicable	<b>PRIMERS</b>	Single and two pack primers.		
<b>MIXING RATIO (V/V)</b>	Single Pack	<b>APPLICATION METHODS</b>	Brush, roller, conventional, airless spray or air assisted spray.		
<b>THINNER</b>	Water				
<b>PRODUCT CODE</b>	647-63108 Structural Green (MTO) 647-63006 Mid Grey (MTO) 647-00806 St Enoch Grey (MTO)				

### Drying characteristics at 50 microns dry film thickness

Temperature	Humidity	Touch	Handle	Full Cure	Overcoat	
					Min	Max
25° C	50%	30 Minutes	2 Hours	7 Days	2 Hours	Indefinite

These figures are given as a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

### TYPICAL SPREADING RATE AT RECOMMENDED DRY FILM BUILD

A spreading rate of 9.0 sq. metres per litre corresponds to 50 microns dry film thickness assuming no losses. Practical spreading rates will vary depending on such factors as method and conditions of application and surface roughness.

# FERREKO® No 5

## TYPICAL SYSTEMS

(The typical systems are offered as a guide only and are not to be used as a specification. It is recommended that the specific needs of a project be discussed with a Dulux Protective Coatings Consultant.)

SURFACE	PREPARATION GUIDE	SYSTEM		DRY FILM THICKNESS
STEEL	Abrasive blast AS1627.4 Class 2	1st Coat	LUXAPRIME® ZP	75 Microns
		2nd Coat	FERREKO® No 5	50 Microns
	Abrasive blast AS1627.4 Class 2.5	1st Coat	ZINCANODE® 304	75 Microns
		2nd Coat	FERREKO® No 5	50 Microns
		3rd Coat	FERREKO® No 5	50 Microns
ALUMINIUM	Clean, degrease and abrade surface	1st Coat	LUXEPOXY® 4 White Primer	50 Microns
		2nd Coat	FERREKO® No 5	50 Microns
		3rd Coat	FERREKO® No 5	50 Microns

**SURFACE PREPARATION** It is recommended that specifiers follow the guidelines for surface preparation from the data sheet for the primer selected. The primer surface must be free from grease, oil, dirt and other loosely adhering materials.

**APPLICATION** Stir each can thoroughly until the contents are uniform. Use of a power mixer is recommended. Remix thoroughly before using and continue mixing during application.

**BRUSH/ROLLER** Apply even coats of the mixed material to the prepared surface. Do not thin. When brushing and rolling additional coats may be required to attain the specified thickness.

**CONVENTIONAL SPRAY** Thin up to 50ml/litre with clean potable water to aid atomisation. Apply in multiple wet coats overlapping each pass 50%. Ensure paint is regularly agitated during application to prevent separation.

Typical Set-up

Graco Delta Gun: 1.4mm (239542)  
 Pressure at Pot: 70-100 kPa (10-15 p.s.i.)  
 Pressure at Gun: 380-410 kPa (55-60 p.s.i.)

**AIRLESS SPRAY** Standard airless spray equipment such as a Graco 33:1 Bulldog with a fluid tip of 19 thou (0.48mm) and an air supply capable of delivering 550-690 kPa (80-100 p.s.i.) at the pump. Remove manifold and gun filters. Thinning is not normally required but up to 50 ml/litre of clean potable water may be added to ease application. Ensure paint is regularly agitated during application to prevent separation.

**PRECAUTIONS** This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. At 25°C and 50% relative humidity, 16 hours drying is required to attain water resistance and 7 days drying to attain full hardness and resistance properties. When overcoating zinc rich coatings ensure that the surface is free of visible moisture or dew. Aluminium containing colours are not recommended for acidic and alkaline conditions. This product is not a decorative coating, and colour variations will occur due to different application techniques. Coatings containing micaceous iron oxide are prone to marring but this will not affect the protective properties.

**CLEAN UP** Clean all equipment with mineral turpentine immediately after use.

**OVERCOATING** Aged coating should be tested for lifting by a method appropriate for the coating thickness, for example 'X' cut or cross-hatch methods. If it lifts, remove it. The surface must be free of oil, grease and other contaminants. High-pressure water wash at 8.3 to 10.3 MPa (1,200 – 1,500 p.s.i.) to remove loosely adhering chalk and dust. Abrasion may be required depending on surface condition.

**SAFETY PRECAUTIONS** **Read Data Sheet, Material Safety Data Sheet and any precautionary labels on containers.**

**STORAGE** Store in well-ventilated cool area. Keep containers closed at all times.

**HANDLING** As with any chemical, ingestion, inhalation and prolonged and repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.

**USING** Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spray painting, users should comply with the provisions of the respective State Spray Painting Regulations.

**FLAMMABILITY** This product is non flammable. On burning will emit toxic fumes.

**WELDING** Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

**MATERIAL SAFETY DATA SHEET is available from Customer Service (132377) or [www.duluxprotectivecoatings.com.au](http://www.duluxprotectivecoatings.com.au)**

Dulux Protective Coatings a division of DuluxGroup (Australia) Pty Ltd  
 1956 Dandenong Road, Clayton 3168  
 A.B.N. 67 000 049 427  
 Dulux, Ferreko, Luxepoxy, Luxaprime and Zincanode are registered trademarks.  
 DuluxGroup is a trademark.

PACKAGING	Available in 15 litre pails
TRANSPORTATION WEIGHT	1.49 kg/litre (Structural Green)
DANGEROUS GOODS	Non Dangerous Goods

Any advice, recommendation, information, assistance or service provided by DULUX Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in coastal areas and for large projects to ensure proper performance.