

# LUXEPOXY<sup>®</sup> UHB

Ultra High Build Epoxy

PC 240

- FEATURES**
- APPLIES TO 3,000 MICRONS IN ONE COAT
  - SOLVENT FREE – DOES NOT REQUIRE THINNING
  - SUITABLE FOR CONTACT WITH FOODSTUFFS

**USES** LUXEPOXY<sup>®</sup> UHB is designed for long life protection of steel and concrete in areas subject to aggressive chemical or marine atmospheres. Due to its tough, abrasion resistant features it is recommended as a single coat protection for oil platform conductors, jacket legs and difficult to maintain seabed installations. It can also be applied to damp concrete surfaces.

LUXEPOXY<sup>®</sup> UHB is ideally suited for the protection of concrete in aggressive chemical environments particularly raw and treated sewerage of an acidic nature.

**SPECIFICATIONS** The use of the film forming components of LUXEPOXY<sup>®</sup> UHB when applied as directed is authorised by Section 175.300 of the U.S. Code of Federal Regulation (Food & Drugs) as the food contact surface of articles intended for use in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting or holding food, subject to the limitation and conditions of use prescribed in that Section.  
AS/NZS 3750.2

## RESISTANCE GUIDE

<b>HEAT RESISTANCE</b>	Up to 120°C dry heat.	<b>ALKALIS</b>	Excellent resistance to splash and spillage of most common alkalis.
<b>WEATHERABILITY</b>	Epoxy coatings may yellow with time. On exterior exposure some chalking may also occur. This will not detract from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	<b>OILS &amp; FATS</b>	Excellent resistance to mineral and vegetable oils and fats excepting for prolonged contact with fatty acids.
<b>SOLVENTS</b>	Suitable for immersion in aromatic and aliphatic hydrocarbons and refined petroleum products.	<b>SALTS</b>	Excellent resistance to neutral and alkali salts.
<b>ACIDS</b>	Suitable for splash and spillage exposure to weak solutions of inorganic acids.	<b>WATER</b>	Excellent resistance to immersion in fresh and salt water.
		<b>ABRASION</b>	Excellent when fully cured.

## TYPICAL PROPERTIES AND APPLICATION DATA

<b>CLASSIFICATION</b>	Two pack epoxy	<b>APPLICATION CONDITIONS</b>	Min	Max	
<b>FINISH</b>	Low Sheen	Air Temperature	10°C	45°C	
<b>COLOUR</b>	Grey (approximate match to AS2700 N35) & limited range of MTO factory made colours.	Substrate Surface Temperature	10°C	45°C	
<b>COMPONENTS</b>	Two	Relative Humidity		85%	
<b>SOLIDS BY VOLUME</b>	100%	Concrete Moisture Content		<10%	
<b>VOC LEVEL</b>	<10 g/L		Min	Max	Recom.
<b>FLASH POINT</b>	Above 65°C	Wet film per coat (microns)	2,000	5,000	3,000
<b>POT LIFE</b>	20 Min (18L, 25°C)	Dry film per coat (microns)	2,000	5,000	3,000
<b>MIXING RATIO (V/V)</b>	Part A : 1      Part B : 1	<b>SUITABLE SUBSTRATES</b>	Abrasive blast cleaned steel or prepared concrete.		
<b>THINNER</b>	<b>Spray</b> Do not Thin	<b>APPLICATION METHODS</b>	Airless spray.		
	<b>Clean up</b> 920-08925      Dulux <sup>®</sup> Epoxy Thinner				
<b>PRODUCT CODE</b>	742-50688      Grey 742-60469      Black (MTO) 976-50689      Hardener				

### Drying characteristics at 3,000 microns dry film thickness

Temperature	Humidity	Touch	Handle	Full Cure	Overcoat	
					Min	Max
10° C	50%	10 Hours	30 Hours	7 Days	30 Hours	48 Hours
15° C	50%	7 Hours	24 Hours	7 Days	24 Hours	36 Hours
25° C	50%	4 Hours	13 Hours	7 Days	13 Hours	24 Hours

These figures are given as a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion. Refer to PRECAUTIONS section for immersion service requirements.

### TYPICAL SPREADING RATE AT RECOMMENDED DRY FILM BUILD

A spreading rate of 0.30 sq. metres per litre corresponds to 3,000 microns dry film thickness assuming no losses. Practical spreading rates will vary depending on such factors as method and conditions of application and surface roughness.

# LUXEPOXY® UHB

## TYPICAL SYSTEMS

(The typical systems are offered as a guide only and are not to be used as a specification. It is recommended that the specific needs of a project be discussed with a Dulux Protective Coatings Consultant.)

SURFACE	PREPARATION GUIDE	SYSTEM		DRY FILM THICKNESS
STEEL	Abrasive blast AS1627.4 Class 3, 75-100 microns profile.	1st Coat	LUXEPOXY® UHB	3,000 Microns
CONCRETE	Clean surface to remove contaminants. Diamond grind, track or light-shot blast. Remove dust.	1st Coat	LUXEPOXY® UHB	500 Microns
		2nd Coat	LUXEPOXY® UHB	2,000 Microns

**SURFACE PREPARATION** Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Rust, millscale, oxide deposits and old paint films on metal surfaces must be removed by abrasive blast cleaning to AS1627.4 Class 3 with a suitable blast media to give a blast profile of 75-100 microns. Remove all dust by brushing or vacuum cleaning.  
Concrete: Remove all laitance, form release, curing compounds, oil, grease and other surface contaminants. Diamond grind, track or light shot-blast to provide suitable profile. Remove all dust by vacuum cleaning. Fill any large voids exposed using Luxepoxy Filler. Cement based substrates should be at least 21 days old before coating.

**APPLICATION** Stir each can thoroughly until the contents are uniform. Use of a power mixer is recommended. Mix the contents of both packs together thoroughly using a power mixer immediately prior to use. Use without further delay. Ensure the clean-up solvent is available before commencing application.

**BRUSH/ROLLER** Suitable for small areas only such as rivets and seams. When brushing and rolling additional coats may be required to attain the specified thickness.

**CONVENTIONAL SPRAY** Not recommended.

**AIRLESS SPRAY** PLURAL COMPONENT AIRLESS UNITS

Airless spray equipment capable of equal volume metering and heating such as a Graco 45:1 or 56:1 Xtreme Mix with a fluid tip of 31 thou (0.79mm, 3 ¼ Twist Tip) or adjustable tip (Titan) and an air supply capable of delivering 690-830 kPa (100-120 p.s.i.) at the pump and a line size of 12 mm I.D.

PRE-MIX AIRLESS APPLICATION

Standard airless spray equipment such as a Graco 68:1 Xtreme with a fluid tip of 31 thou (79mm) and an air supply capable of delivering 690-830 kPa (100-120 p.s.i.) at the pump and a line size of 12mm I.D. Add the stirred components together in the supplied 1:1 ratio by volume and mix using a power mixer immediately prior to use. Use without further delay.

**PRECAUTIONS** This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® representative for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Freshly mixed material must not be added to material that has been mixed for some time. The rate of cure is dependent upon temperature. Do not apply at temperatures below 10°C. Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. Concrete tanks will need to be emptied in advance of coating application to allow the moisture content of the concrete to fall below the maximum of 12%. After the coating has cured, check for defects in the coating in accordance with AS 3891.4, and repair. Do not apply over water proofing compounds. The coating MUST be fully cured prior to being placed under immersion conditions. This material MUST NOT be thinned.

**CLEAN UP** Clean all equipment with Dulux® Epoxy Thinner (920-08925) immediately after use.

**OVERCOATING** Aged coating should be tested for lifting by a method appropriate for the coating thickness, for example 'X' cut or cross-hatch methods. If it lifts, remove it. The surface must be free of oil, grease and other contaminants. High-pressure water wash at 8.3 to 10.3 MPa (1,200 - 1,500 p.s.i.) to remove loosely adhering chalk and dust. Abrasion may be required depending on surface condition. If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

**REPAIR** Within 24 hours at 25°C: Thoroughly solvent wash with Epoxy Thinner, allow the solvent to flash off and apply LUXEPOXY® UHB to the prepared area, overlapping sound coating by 70-100mm.

After 24 hours at 25°C: Sweep blast or abrade by hand (Grade 150 or coarser) and then solvent wash using Epoxy Thinner for areas of low film build or pin holes. Apply LUXEPOXY® UHB to the prepared area, overlapping sound coating by 70-100mm.

**SAFETY PRECAUTIONS** **Read Data Sheet, Safety Data Sheet and any precautionary labels on containers.**

**STORAGE** Store in well-ventilated area under cover. Keep containers closed at all times.

**HANDLING** As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.

**USING** Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spray painting, users should comply with the provisions of the respective State Spray Painting Regulations.

**FLAMMABILITY** This product is combustible. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO<sub>2</sub> or dry chemical powder. On burning will emit toxic fumes.

**WELDING** Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

**SAFETY DATA SHEET is available from Dulux Customer Service (Australia 132 377 or New Zealand 0800 800 424)**  
[www.duluxprotectivecoatings.com.au](http://www.duluxprotectivecoatings.com.au)

Dulux Protective Coatings a division of		PACKAGING	Available in 18 litre packs
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118	TRANSPORTATION WEIGHT	1.14 kg/litre (Average of components)
Dulux and Luxepoxy are registered trade marks of DuluxGroup (Australia) Pty Ltd.		DAANGEROUS GOODS	Part A: Non Dangerous Goods Part B: Non Dangerous Goods

Any advice, recommendation, information, assistance or service provided by DULUX Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in coastal areas and for large projects to ensure proper performance.